

Transparent polyamides /透明尼龙

性 能 Properties	测试方法 Test method	单位 Unit	数 值 Value
<b>Mechanical properties /机械性能</b>			
Tensile test /拉伸测试 23°C 50mm/min Stress at yield $\sigma_S$ /屈服强度 $\sigma_S$ Strain at yield $\epsilon_S$ /屈服拉伸率 $\epsilon_S$ Nominal strain at break $\epsilon_B$ /断裂伸长率 $\epsilon_B$	ISO 527-1/2	MPa % %	90 8 >50
Tensile test /拉伸测试 23°C 5mm/min Tensile strength $\sigma_B$ /拉伸强度 $\sigma_B$ Nominal strain at break $\epsilon_B$ /断裂伸长率 $\epsilon_B$	ISO 527-1/2	MPa %	
Tensile modulus/拉伸模量 23°C Tensile creep modulus /拉伸蠕变模量 1h 100-h	ISO 527-1/2 ISO 899-1	MPa MPa	2800 2300 1100
Flexural test /弯曲测试 5mm/min Flexural strength $\sigma_{B\text{b}}$ /弯曲强度 $\sigma_{B\text{b}}$ Flexural strength at 3.5% strain $\sigma_{B3.5}$ /弯曲强度(3.5%应变) $\sigma_{B3.5}$ Outer fiber strain at maximum stress $\epsilon_{B\text{b}}$ /最大应力时外力应变 $\epsilon_{B\text{b}}$ Outer fiber strain at break $\epsilon_{B\text{bR}}$ /断裂时外力应变 $\epsilon_{B\text{bR}}$	ISO 178	MPa MPa % %	152 104 9 n.r.
Flexural modulus /弯曲模量	ISO 178	MPa	3000
CHARPY impact strength /悬臂梁冲击强度 23°C 0°C -30°C	ISO 179/1eU	kJ/m <sup>2</sup> kJ/m <sup>2</sup> kJ/m <sup>2</sup>	N N N
CHARPY notched impact strength /悬臂梁冲击强度(缺口) 23°C 0°C -30°C	ISO 179/1eA	kJ/m <sup>2</sup> kJ/m <sup>2</sup> kJ/m <sup>2</sup>	12C 10C 7C
Shore hardness D /邵氏硬度D	ISO 868		87
Ball indentation hardness H30 /球缺口硬度H30	ISO 2039-1	N/mm <sup>2</sup>	155
<b>Physical and Thermal Properties /物理和热性能</b>			
Density /密度 23°C	ISO 1183	g/cm <sup>3</sup>	1.12
Viscosity number /粘数	ISO 307	cm <sup>3</sup> /g	132
Vicat softening temperature /维卡软化温度 Method A /方法A Method B /方法B	ISO 306	°C °C	148 150
Temperature of deflection under load /荷载变形温度 Method A /方法A Method B /方法B	ISO 75-1/2	°C °C	120 140
Linear thermal expansion /热线性伸展 longitudinal $\alpha_{B\text{II}}$ /纵向 $\alpha_{B\text{II}}$ transverse $\alpha_{\perp}$ /横向 $\alpha_{\perp}$	ISO 11359	10 <sup>-4</sup> K <sup>-1</sup> 10 <sup>-4</sup> K <sup>-1</sup>	0.54 0.53
Glass transition temperature T <sub>g</sub> /熔点(DSC)	10k/min	°C	153
Melt temperature (DSC) /熔点(DSC)	10k/min	°C	
<b>Electrical properties /电性能</b>			
Relative permittivity $\epsilon_r$ /相对介电率 23°C 50Hz 100Hz 1MHz	IEC 60250		4.2 4.6 3.4
Dissipation factor tan δ /分散因数δ 23°C 50Hz 100Hz 1MHz	IEC 60250		0.021 0.025 0.028
Electric strength E <sub>d</sub> /电强度 E <sub>d</sub>	K20/P50	IEC 60243-1	kV/mm
Comparative tracking index /相对漏电跟踪指数 Test solution A /测试溶液A	CTI 100-drops value	IEC 60112	>600
Glow wire test /发热电线测试	thickness=1mm	IEC 60695-2-1/0-3	°C
Volume resistivity $\rho_d$ /体积电阻率 $\rho_d$	IEC 60093	Ohm m	>10 <sup>13</sup>
Spec.surface resistance $\rho_s$ /表面电阻系数 $\rho_s$	IEC 60093	Ohm	>10 <sup>15</sup>
Surface resistance R <sub>OA</sub> /表面电阻 R <sub>OA</sub>	IEC 60093	Ohm	>10 <sup>13</sup>

N=no break /无断裂 C=complete /完全断裂 n.r.=not reached /没有达到

本资料提供出于诚意，但绝对无明确或默认的保证，因此明聚塑胶有限公司并不为此承担任何责任和义务。

The information contained is believed to be reliable, but no warranties, express or implied, including the implied warranties of merchantability or fitness for a particular purpose.



明聚塑胶  
Mingju PLASTICS  
www.mingjuplastics.com